



ALMATIS

PREMIUM ALUMINA



Global Product Data

AFL Aluminas

Product	AFL 1	AFL 13
Chemical Analysis [%]	typical	typical
Al ₂ O ₃	87 - 89	≤ 99
Na ₂ O	≤ 0.30	≤ 0.30
Fe ₂ O ₃	≤ 0.07	≤ 0.05
SiO ₂	≤ 0.12	≤ 0.12
MgO	10 - 12	≤ 0.30
CaO	≤ 0.30	≤ 0.08
Mineralogical composition		
α-Alumina	xxx	xxx
Spinel	xxx	–
Periclase	–	–
Grain size distribution		
> 1.0 mm	≤ 1	≤ 1
< 0.250 mm	55 - 60	80 - 85
Surface Area BET [m ² /g]	1.0 - 2.0	1.0 - 2.0

All data are based upon Almatris standard test methods.
The typical properties are based upon the actual averages from production data.

Think alumina, think Almatris.



AFL-Aluminas

The Almatris AFL Aluminas are specifically designed as the main component in the formulation of a fine, free flowing infiltration castable, for use in the InfilCast® system. Their fine particle size distribution, of up to 1 mm, allows optimised infiltration flow to fill the voids between the coarse Tabular T-60 or Magnesium Aluminate Spinel AR-90 aggregates. The different mineral composition of the various AFL Aluminas enable the development of a matrix system with high refractoriness and corrosion resistance to meet the individual requirements of high performance refractory products. For the specially formulated fine infiltration castable products, the AFL Aluminas are used together with Calcium Aluminate Cement, ie. CA-270 as the binder, and the Almatris Dispersing Aluminas ADS 1, ADS 3 and ADW 1. This combination of raw materials provides optimum castable dispersion with reduced water demand. Also setting times can be adjusted according to the specific placement requirements and climatic conditions.



Contacts for sales, technical information and application assistance

Almatris GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

Phone

49 621 5707 0

Fax

49 621 5707 130**Almatris B.V.**

Theemsweg 30
3197KM Botlek RT
The Netherlands

Phone

31 181 2701 00

Fax

31 181 2178 53**Almatris, Inc.**

501 West Park Road
Leetsdale, PA 15056, USA

General Phone

800 643 8771

Phone

1 412 630 2800

Fax

1 412 630 2900**Qingdao Almatris Co., Ltd.**

F15, Sunshine Tower
61 Hongkong Middle Road
Qingdao, 266071
P.R. China

Phone

86 532 8572 8035

Fax

86 532 8572 8551**Qingdao Almatris Trading Co., Ltd.**

Room 1807, Eton Place
69 Dong Fang Road
Shanghai, 200120
P.R. China

Phone

86 21 5879 4987

Fax

86 21 5879 6502**Qingdao Almatris Co., Ltd.**

4W-W-# 9 building
Jiming Blocks, Kaifaque
Kaifeng, Henan
P.R. China

Phone

86 378 3850 485

Fax

86 378 3850 485**Headquarters**

Almatris GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone **49 69 957 341 0**Fax **49 69 957 341 13**

info@almatris.com
www.almatris.com

Almatris Alumina Private Limited

Kankaria Estate
2nd Floor
6, Little Russell Street
Calcutta 700-071, India

Phone

91 33 2289 4694

Fax

91 33 2289 4693**Almatris Limited**

Morimura Bldg.
1-3-1 Toranomou
Minato-ku, Tokyo 105-8451
Japan

Phone

81 3 3502 2371

Fax

81 3 3502 2375**MSDS 1018**