



ALMATIS

PREMIUM ALUMINA



Global Product Data

Global Almatis Aluminas for Refractories Applications

Properties/method	Unit	CT 800 FG			T60/T64–20 micron*		
		typical	Min	Max	typical	Min	Max
Specific Surface Area/BET	[m ² /g]	0.9	0.7	1.2			
Particle Size/+0.020mm	[%]				5.0	0	10.0
Particle Size/D50 Cilas	[µm]	3.5	2.5	5.0	2.0		3.1
Particle Size/wet sieve >45µm	[%]	0.1		3.0			
Chemical Analysis							
Al ₂ O ₃	[%]	99.7			99.3		
Na ₂ O	[%]	0.12		0.15			0.40
Fe ₂ O ₃	[%]	0.02		0.04			
Fe Magnetic	[%]						0.02
SiO ₂	[%]	0.02		0.04			0.15
CaO	[%]	0.02					

*T60/T64–20 micron MSDS154.

All data are based upon Almatis standard test methods.

The typical properties are based upon the actual averages from production data.

Think alumina, think Almatis.

GP-RCP/018/R03/O608/MSDS 154/387



Global Almatis Aluminas for Refractories Applications

Properties/method	Unit	RG 4000			CL 370			E-SY 1000		
		typical	Min	Max	typical	Min	Max	typical	Min	Max
Specific Surface Area/BET	[m ² /g]	7.2	6.0	9.5	3.0	2.6	3.4	2.0	1.6	2.3
Particle Size/D50 Cilas	[µm]	0.6	0.4	0.8	2.5	1.8	3.0	1.7	1.3	2.1
Particle Size/D90 Cilas	[µm]	3.0		4.0	7.0	5.0	10.0	8.0	5.0	12
Grain Size Distribution		mono-modal			bi-modal			bi-modal		
Chemical Analysis										
Al ₂ O ₃	[%]	99.8			99.7			99.5		
Na ₂ O	[%]	0.08		0.10	0.10		0.14	0.20		0.35
Fe ₂ O ₃	[%]	0.02		0.04	0.03		0.04	0.03		0.06
SiO ₂	[%]	0.03		0.08	0.03		0.07	0.03		0.06
CaO	[%]	0.02			0.02			0.02		

All data are based upon Almatis standard test methods.

The typical properties are based upon the actual averages from production data.



Global Almatís Aluminas for Refractories Applications

Properties/method	Unit	CTC 20			CTC 40			CTC 50		
		typical	Min	Max	typical	Min	Max	typical	Min	Max
Specific Surface Area/BET	[m ² /g]	2.0	1.5	3.0	4.8	4.0	5.5	4.1	3.7	5.5
Particle Size/D50 Cilas	[µm]	1.8	1.4	2.3	1.2	0.8	1.5	1.5	1.1	1.9
Particle Size/D90 Cilas	[µm]	4.5		6.0	5.5	4.7	6.8	7.5	6.0	9.0
Grain Size Distribution		mono-modal			bi-modal			multi-modal		
Chemical Analysis										
Al ₂ O ₃	[%]	99.7			99.8			99.7		
Na ₂ O	[%]	0.12		0.20	0.08		0.12	0.16		0.20
Fe ₂ O ₃	[%]	0.03		0.05	0.03		0.06	0.03		0.05
SiO ₂	[%]	0.03		0.08	0.03		0.07	0.03		0.10
CaO	[%]	0.02			0.03			0.03		

All data are based upon Almatís standard test methods.

The typical properties are based upon the actual averages from production data.



Global Almatis Aluminas for Refractories Applications



Contacts for sales, technical information and application assistance

Almatis GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

Phone
49 621 5707 0
Fax
49 621 5707 130

Almatis B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

Phone
31 181 2701 00
Fax
31 181 2178 53

Almatis, Inc.

501 West Park Road
Leetsdale, PA 15056, USA

General Phone
800 643 8771
Phone
1 412 630 2800
Fax
1 412 630 2900

Qingdao Almatis Co., Ltd.

F15, Sunshine Tower
61 Hongkong Middle Road
Qingdao, 266071
P.R. China

Phone
86 532 8572 8035
Fax
86 532 8572 8551

Qingdao Almatis Trading Co., Ltd.

Room 1807, Eton Place
69 Dong Fang Road
Shanghai, 200120
P.R. China

Phone
86 21 5879 4987
Fax
86 21 5879 6502

Qingdao Almatis Co., Ltd.

4W-W-# 9 building
Jiming Blocks, Kaifaque
Kaifeng, Henan
P.R. China

Phone
86 378 3850 485
Fax
86 378 3850 485



Headquarters

Almatis GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone **49 69 957 341 0**
Fax **49 69 957 341 13**

info@almatis.com
www.almatis.com

Almatis Alumina Private Limited

Kankaria Estate
2nd Floor
6, Little Russell Street
Calcutta 700-071, India

Phone
91 33 2289 4694
Fax
91 33 2289 4693

Almatis Limited

Morimura Bldg.
1-3-1 Toranomom
Minato-ku, Tokyo 105-8451
Japan

Phone
81 3 3502 2371
Fax
81 3 3502 2375

MSDS 154/387