



ALMATIS

PREMIUM ALUMINA



## Global Product Data


# Almatris Hydral<sup>®</sup> Coat 7

Almatris Hydral Coat 7 is a white aluminum trihydroxide  $\text{Al}(\text{OH})_3$ . It is a specially precipitated high-purity white aluminum trihydroxide powder with a Z percent brightness value of 99+. It has an extra-fine, uniform median particle size of about 0.7 microns in diameter. Hydral Coat 7 powder is a fully deagglomerated powder.

Hydral Coat 7 is halogen-free and finds wide application as a low-smoke, flame-retardent filler in thermoset and thermoplastic materials. It improves arc-track resistance in many plastics used in electrical applications.

As a reinforcing pigment in adhesives and adhesive tapes, Hydral Coat 7 improves cold flow properties, maintains the neutrality or alkalinity of the composition, and increases cohesion.

Typical Particle Size Analysis by Sedigraph



Think alumina, think Almatris.

GP-SH/008/R05/1207/MSDS 839



## Almatis Hydral Coat® 7

Product	Hydral Coat 7		
	Average	Shipping <sup>(1)</sup>	Test Methods
<b>Chemical Composition (%)</b>			
SiO <sub>2</sub>	0.005	-	DC Arc Optical Emissions Spectrometry
Fe <sub>2</sub> O <sub>3</sub>	0.006	-	DC Arc Optical Emissions Spectrometry
Na <sub>2</sub> O (total)	0.24	-	DC Arc Optical Emissions Spectrometry
Na <sub>2</sub> O (soluble)	0.04	0.08	Flame Emission Photometry
Al(OH) <sub>3</sub>	99.6	-	Difference
Moisture	0.38	0.60	Microwave
<b>Physical Properties</b>			
Loose bulk density (g/cm <sup>3</sup> )	0.38	-	Modified ASTM B212-89
Packed bulk density (g/cm <sup>3</sup> )	0.53	-	Modified ASTM B527-85
Surface area (m <sup>2</sup> /g)	8.6	-	Brunauer-Emmett-Teller Nitrogen Adsorption
Brightness (% Z)	99.2	-	Z value of the XYZ Tristimulus divided by 1.18103
Refractive index	1.57	-	
Mohs hardness	2.5-3.5	-	
Electrical conductivity (µS/cm)	<200	-	Modified ISO787-14 (10%)
<b>Particle Size</b>			
% on 325 mesh	0.003	-	Wet Screen
d <sub>95</sub> (µ)	1.60	-	Sedigraph 5100
d <sub>50</sub> (µ)	0.70	0.64-0.76	Sedigraph 5100
d <sub>10</sub> (µ)	0.35	-	Sedigraph 5100

(1) Almatis general shipping specifications

2002 Data

All data are based upon Almatis standard test methods, and all test methods are available upon request.

Unless stated otherwise values are typical.

### Contacts for sales, technical information and application assistance

#### Almatis GmbH

Lyoner Straße 9  
60528 Frankfurt/Germany

Phone  
**49 69 957 341 0**

Fax  
**49 69 957 341 13**

#### Almatis, Inc.

501 West Park Road  
Leetsdale, PA 15056  
USA

Phone (within US)  
**1 800 643 8771**

Phone (outside US)  
**1 412 630 2800**

Fax  
**1 412 630 2900**

#### Qingdao Almatis Co., Ltd.

15F, Sunshine Tower  
61 Hongkong Middle Road  
Qingdao, 266071, China

Phone  
**86 532 8572 8035**

Fax  
**86 532 8572 8551**

#### Almatis Limited

Morimura Bldg.  
1-3-1 Toranomom  
Minato-ku, Tokyo 105-8451

Japan  
Phone  
**81 3 3502 2371**

Fax  
**81 3 3502 2375**

#### Almatis Headquarters

Lyoner Straße 9  
60528 Frankfurt/Germany

Phone **49 69 957 341 0**

Fax **49 69 957 341 13**

[info@almatis.com](mailto:info@almatis.com)  
[www.almatis.com](http://www.almatis.com)

## MSDS 839