



ALMATIS

PREMIUM ALUMINA



Provisional Product Data

E-SY 2000 - with Spinel

Chemical Composition		typical
Al ₂ O ₃ by difference	[%]	88.0
MgO	[%]	11.0
Na ₂ O	[%]	0.1
Fe ₂ O ₃	[%]	0.08
SiO ₂	[%]	0.04

Properties / method	typical
Specific surface area / BET	2.3 m ² /g
Particle Size / D50 Cilas	1.4 μm
Particle Size / D90 Cilas	6.5 μm

All data are based upon Almatris standard test methods.
The typical properties are based upon the actual averages from production data.

Think alumina, think Almatris.

PP-RCP/005/R06/0413/MSDS 1000



E-SY 2000 - with Spinel

Standard Packaging

- 25 kg paperbags on 1 mt pallet
- 1000 kg bigbag, discharge sleeve and shrink wrapped



Contacts for sales, technical information and application assistance

Almatris GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

☎ 49 621 5707 0
☎ 49 621 5707 130

Qingdao Almatris Co., Ltd.

F15, Sunshine Tower
61 Hongkong Middle Road
Qingdao, 266071
P.R. China

☎ 86 532 8572 8035
☎ 86 532 8572 8551

Almatris B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

☎ 31 181 2701 00
☎ 31 181 2178 53

Qingdao Almatris Trading Co., Ltd.

Room 1807, Eton Place
69 Dong Fang Road
Shanghai, 200120
P.R. China

☎ 86 21 5879 4987
☎ 86 21 5879 6502

Almatris, Inc.

501 West Park Road
Leetsdale, PA 15056, USA

☎ 800 643 8771 General
☎ 1 412 630 2800
☎ 1 412 630 2900

Almatris do Brasil Ltda.

Avenida Jose de Souza
Campos, 243
2° Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

☎ 55 19 3515-1400
☎ 55 19 3515-1410



Almatris GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatris.com
www.almatris.com

Almatris Alumina Private Limited

Kankaria Estate
2nd Floor
6, Little Russell Street
Kolkata 700-071, India

☎ 91 33 2289 4694
☎ 91 33 2289 4693

Almatris Limited

Morimura Bldg.
1-3-1 Toranomon
Minato-ku, Tokyo 105-8451
Japan

☎ 81 3 3502 2371
☎ 81 3 3502 2375