



Global Product Data

T-162 Tabular Alumina Balls





T-162 Tabular Alumina Balls

Product Characteristics

T-162 Tabular Alumina Balls are high-purity sintered alpha-alumina spheres (in various sizes). This product has been fired at extremely high temperatures (>1900°C) to reduce porosity to a very low level. This high-temperature process leads to the growth of large plate-like (or tablet-like) alpha-alumina crystals giving "tabular" alumina its name. T-162 Tabular Alumina Balls are carefully selected before packaging for size control, roundness and smooth surface. Some chipped, broken, oblong and rough surface balls may be present in all sizes.

Product Applications

T-162 Tabular Alumina Balls have been used since the 1950s for heat exchange media (so-called pebble heaters) and metal filtration. The properties of smooth surface, chemical inertness, high chemical purity and superior thermal and mechanical shock resistance are crucial to the excellent performance of T-162 in these applications.

T-162 Tabular Alumina Balls

Chemical Composition [wt %]		Typical
Al ₂ O ₃ by difference		99.7
SiO ₂		0.02
Fe ₂ O ₃		0.02
Na ₂ O		0.20
Physical Properties		
Specific Gravity		3.65
Apparent Porosity [%]		1.5
Water Absorption [%]		0.4
Packed Bulk Density [kg/m ³]	2160 (for 3/16") to 2000 (for 1")	
Cold Crushing Strength [N]	2900 (for 3/16") to 14700 (for 1")	

Sizes	Nom. Diameter	Size Distribution		
		10 % max.	80 % min.	10 % max.
1 inch	25 mm	+ 26.5 mm	26.5 – 23.5 mm	– 23.5 mm
3/4 inch	19 mm	+ 20.0 mm	20.0 – 18.0 mm	– 18.0 mm
1/2 inch	13 mm	+ 14.0 mm	14.0 – 12.0 mm	– 12.0 mm
3/8 inch	11 mm	+ 12.0 mm	12.0 – 10.0 mm	– 10.0 mm
5/16 inch	8 mm	+ 9.0 mm	9.0 – 7.0 mm	– 7.0 mm
1/4 inch	6.4 mm	+ 7.0 mm	7.0 – 5.5 mm	– 5.5 mm
3/16 inch	4.8 mm	+ 5.5 mm	5.5 – 4.0 mm	– 4.0 mm

All data are based upon Almatis standard test methods.

The typical properties are based upon the actual averages from production data.

Standard Packaging

- 25 kg paper bags
- 1000 kg bulk bags



T-162 Tabular Alumina Balls



Contacts for sales, technical information and application assistance

Almatris GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

☎ 49 621 5707 0

☎ 49 621 5707 130

Almatris B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

☎ 31 181 2701 00

☎ 31 181 2178 53

Almatris, Inc.

501 West Park Road
Leetsdale, PA 15056, USA

☎ 800 643 8771 General

☎ 1 412 630 2800

☎ 1 412 630 2900

**Qingdao Almatris
Co., Ltd.**

F15, Sunshine Tower
61 Hongkong Middle Road
Qingdao, 266071
P.R. China

☎ 86 532 8572 8035

☎ 86 532 8572 8551

**Qingdao Almatris Trading
Co., Ltd.**

Room 1807, Eton Place
69 Dong Fang Road
Shanghai, 200120
P.R. China

☎ 86 21 5879 4987

☎ 86 21 5879 6502

Almatris do Brasil Ltda.

Avenida Jose de Souza
Campos, 243
2º Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

☎ 55 19 3515-1400

☎ 55 19 3515-1410



Almatris GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatris.com
www.almatris.com

**Almatris Alumina
Private Limited**

Kankaria Estate
2nd Floor
6, Little Russell Street
Kolkata 700-071, India

☎ 91 33 2289 4694

☎ 91 33 2289 4693

Almatris Limited

Morimura Bldg.
1-3-1 Toranomon
Minato-ku, Tokyo 105-8451
Japan

☎ 81 3 3502 2371

☎ 81 3 3502 2375

MSDS 154