



Provisional Product Data

RAPOL

Rapid Alumina Polishing

Aluminum oxide is the most widely used polishing medium. As an inorganic product, it has one important advantage over natural materials used for polishing: the physical properties and chemical compositions are constant regardless of the pressure or temperature experienced during use.

The RAPOL range is especially designed for one step polishing processes, which gives "rapid" cutting and shiny polishing performance. The product enables our customers to offer cost efficient solutions for the end user.

Product / Properties Ground	Unit	RAPOL 100 typical	RAPOL 500 typical
Calcination degree		low	low
Primary crystal size	µm	0.3	0.3
Al ₂ O ₃ content	[%]	99	99
Chemical Analysis			
Na ₂ O	[%]	0,1	0.1
Fe ₂ O ₃	[%]	0.02	0.02
Particle Size			
> 90 µm	[%]		0.1
> 63 µm	[%]	50-95	1
Particle size D50	µm	70	15
Specific surface area/BET	m ² /g	3.5	4
Loose bulk density	g/l		600
Oil absorption	[%]	45	35
Cutting effect		6	3
Polishing effect		7	9

All data are based upon Almatris standard test methods.

The typical properties are based upon the actual averages from production data.



RAPOL Rapid Alumina Polishing

Standard Packaging

- 25 kg bags
- 750 kg big bag, discharge sleeve and shrink wrapped



Contacts for sales, technical information and application assistance

Almatis GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

Phone
49 621 5707 0
Fax
49 621 5707 130

Almatis B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

Phone
31 181 2701 00
Fax
31 181 2178 53

Almatis Alumina Private Limited

Kankaria Estate, 2nd Floor
6, Little Russell Street
Calcutta 700-001, India

Phone
91 33 2242 7961
Fax
91 33 2242 1557

Qingdao Almatis Co. Ltd.

No.1 Song Hua Jiang Road
Qingdao Economic &
Technology Development Zone
Qingdao, 266510
P.R. China

Phone
+86 532 8572 8035
Fax
+86 532 8572 8551

Almatis Limited

Morimura Bldg.
1-3-1 Toranomom
Minato-ku,
Tokyo 105-0003
Japan

Phone
81 3 5510 66 88
Fax
81 3 5510 66 80



Almatis GmbH

Lyoner Straße 9
60528 Frankfurt/Germany

Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatis.com
www.almatis.com

Almatis, Inc.

501 West Park Road
Leetsdale, PA 15056,
USA

General Phone
800 643 8771
Phone
1 412 630 2800
Fax
1 412 630 2900

Almatis do Brasil Ltda.

Avenida Jose de Souza
Campos, 243
2º Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

Phone
55 19 3515-1400
Fax
55 19 3515-1410

SDS 387