



Product Data

BSA 96





BSA 96

Chemical Composition		Typical	Min.	Max.
Al ₂ O ₃	[%]	97.0	95.5	
TiO ₂	[%]	1.5		2.0
SiO ₂	[%]	0.5		1.0
MgO	[%]	0.2		0.4
Na ₂ O	[%]	0.3		0.4
Fe ₂ O ₃	[%]	0.15		0.3
Fe Magnetic	[%]			0.02

Physical Properties		Typical	Min.	Max.
Bulk Specific Gravity	[g/cm ³]	3.5	3.45	
Apparent Porosity	[%]	4.5		6.0
Water Absorption	[%]	1.3		1.8

All data are based upon Almatris standard test methods.

Available sizes DIN ¹⁾	Typical [%]	Min/Max [%]
6 – 15 mm		
+ 16.0 mm		0 - 1
+ 12.5 mm	7	
+ 10.0 mm	25	
+ 6.3 mm	60	
- 6.3 mm		0 - 10
5 – 8 mm		
+ 8.0 mm		0 - 10
+ 6.3 mm	53	
+ 5.0 mm	38	
- 5.0 mm		0 - 10
3 – 6 mm		
+ 6.3 mm		0 - 4
+ 5.0 mm	28	
+ 4.0 mm	35	
+ 3.35 mm	20	
+ 2.0 mm	16	
- 2.0 mm		0 - 3

Available sizes DIN ¹⁾	Typical [%]	Min/Max [%]
1 – 3 mm		
+ 3.35 mm		0 - 8
+ 2.0 mm	58	
+ 1.0 mm	40	
- 1.0 mm		0 - 10
0 – 1 mm		
+ 1.4 mm		0 - 2
+ 1.0 mm	5	
+ 0.50 mm	22	
+ 0.212 mm	21	
+ 0.106 mm	32	
- 0.106 mm		5 - 26
0.5 – 1 mm		
+ 1.4 mm		0 - 2
+ 1.0 mm	15	
+ 0.71 mm	58	
+ 0.5 mm	25	
- 0.5 mm		0 - 10

Available sizes DIN ¹⁾	Typical [%]	Min/Max [%]
0 – 0.5 mm		
+ 0.50 mm	3	
+ 0.250 mm	14	
+ 0.125 mm	30	
+ 0.045 mm	42	
- 0.045 mm	11	
- 90 micron		
+ 0.090 mm		0 - 5
+ 0.063 mm	10	
- 0.063 mm		75 - 100

1) Sieve Analysis as per DIN/ISO 3310/1

Product Information

- High temperature sintered aggregate
- Innovative European raw material alternative for BFA and high quality bauxite
- Homogenous product with no metallic impurities or carbides
- Cost advantage due to lower BSG compared to fused aggregates

Packaging

- 1 mt big bags
- 25 kg bags



Contacts for sales, technical information and application assistance



ALMATIS
PREMIUM ALUMINA

Almatris GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone **49 69 957 341 0**
Fax **49 69 957 341 13**

info@almatris.com
www.almatris.com

Almatris GmbH
Giulinistrasse 2
67065 Ludwigshafen
Germany

☎ **49 621 5707 0**
☎ **49 621 5707 130**

Almatris B.V.
Theemsweg 30
3197KM Botlek RT
The Netherlands

☎ **31 181 2701 00**
☎ **31 181 2178 53**

Almatris do Brasil Ltda.
Avenida Jose de Souza
Campos, 243
2° Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

☎ **55 19 3515-1400**
☎ **55 19 3515-1410**

SDS 2008