








Product Introduction

Calcined Aluminas

Alumina is one of the most important abrasive materials for polishing a wide range of surfaces. Considering the diverse customer needs for different applications, Almatis strives to find premium solutions to enable our customers to combine highest cutting rates and brilliant finishing results.

Almatis offers the broadest polishing portfolio in the industry and with this wide selection we offer the most efficient solution for each customer's specific need.



APPLICATION	ULTIMATE- SERIES	P- SERIES	RAPOL- SERIES	PSG- SERIES	GILOX- SERIES
Metal pre-polishing		Х		Х	Х
Metal finishing	Х	Х		Х	
Aluminum		Х		Х	Х
Plastic/Paint/Resin	Х	Х	Х		
Wood		Х			
Stones		Х		Х	Х
Electronics					Х
Cleaners	Х	Х	Х		
Brake pads		Х		Х	Х
Jewelry	Х	Х	Х		

GP_007/R02/1022/SDS 387 Page 02 of 08



PSG-Series

Metal polishing is the largest polishing application for Almatis premium aluminas. To achieve high surface quality, a two-step approach is suggested. For the prepolishing step, Almatis supplies a hard calcined PSG series with surface areas $<1.1\,\mathrm{m}^2/\mathrm{g}$ and clearly defined top cuts.

The goal of pre-polishing operations is to achieve the highest possible abrasiveness together with a well-prepared surface. High performance pre-polishing compounds reduce the time and cost necessary for the final polishing steps by providing a surface with low roughness values.



SEM PSG-Series

Chemical Composition	Unit			All Sizes	(Typicals)		
Al ₂ O ₃ by difference	[%]			99).7		
Na ₂ O	[%]			0	.1		
SiO ₂	[%]			0.	02		
Calcination Degree				hi	gh		
Primary Crystal Size	(µm)			;	3		
α- A-l ₂ O ₃ Content	[%]	99					
Particle Size		PSG 100	PSG 125	PSG 140	PSG 180	PSG 200	PSG 300
≥ 425 µm / 35 mesh	[%]	0.0	0.0	0.0			
\geq 200 μm / 65 mesh	[%]	≤]			0		
≥125 µm / 120 mesh	[%]		≤ 4	≤ 0.5		≤ 0.5	
\geq 90 μm / 170 mesh	[%]			≤ 5			
\geq 63 μm / 250 mesh	[%]	50 - 95	30 - 60	10-35		3 – 15	
\geq 45 μm / 325 mesh					20 - 40		≤]
D50 Typical	[µm]	75	60	50	10	6	4.5
Physical Properties							
Specific Surface Area	[m²/g]	≤ 0.7	≤ 0.7	≤ 0.7	≤ 1.0	≤ 1.0	≤].]
Loose Bulk Density	[g/l]	800 - 1050	800 - 1050	700 - 1000	700 - 950	760 - 950	550 - 900
Oil Absorption	[%]	41 - 54	35 - 50	35 - 50	12 - 25	14 - 25	12 - 22



Calcined Aluminas for Polishing GILOX-Series

For applications targeting for very high cut Almatis products of the GILOX-Series are the right solution. By manipulating crystal size and shape using different processing routes, Almatis can offer a wide range of products with unique cut rates. Another specialty is the transparency and plate-like structure of our products P 20 and P 25, which stay stable during milling process and can be used in special polishing applications as well as wear resistant coatings


Chemical Composition	Unit	PBC	P 20	P 25	GILOX 125	GILOX 63	BSA 96 -90µm	T60/T64 -45μm
Al ₂ O ₃ by difference	[%]	≥ 99.5	≥ 99.5	≥ 99.5	≥ 99.5	≥ 99.5	≥ 96	≥ 99.5
Na ₂ O	[%]	0.1	0.3	0.35	0.35	0.35	0.3	0.3
SiO ₂	[%]	0.02	0.03	0.03	0.03	0.03	0.5	0.05
Calcination Degree		high	very high	very high	very high	very high	very high	very high
Primary Crystal Size	[µm]	4.5	18	22	15	15		
$lpha$ - A-l $_2$ O $_3$ Content	[%]				99			
Particle Size								
≥150 µm / 100 mesh	[%]	≤ 3						
\geq 125 μm / 120 mesh	[%]				≤]			
\geq 90 μm / 170 mesh	[%]						≤ 5	
\geq 63 μm / 250 mesh	[%]	40 - 90	50 - 80	55 – 90	5 – 12	0.1 - 3	0 - 25	≤]
\geq 45 μm / 325 mesh	[%]							≤ 5
D50 Typical	[µm]	65	15*	25*	22	17		8
Physical Properties								
Specific Surface Area	[m²/g]	0.3-0.45	0.15	0.15	0.2	0.2		
Loose Bulk Density	[g/l]	800 - 1100	600 – 1100	600 - 1100				
Oil Absorption	[%]	35 - 50	20-60	25 – 65	15 - 30	10-25		

^{*}de-agglomerated





SEM of Tabular Alumina T60/T64, -45µm



Transparency of P 25 crystals



P-Series

For finishing of all kinds of surfaces, Almatis supplies a broad portfolio with unique performance in the $9-17~\text{m}^2/\text{g}$ surface area range. Almatis can offer optimum cutting solutions, as well as polishing and brightening, for customer specific needs.

Chemical Composition	Unit				All	Sizes (Typic	als)			
Al ₂ O ₃ by difference	[%]					≥ 99.5				
Na ₂ O	[%]					0.4				
SiO ₂	[%]					0.01				
Calcination Degree						low				
Primary Crystal Size	(µm)					≤]				
α- A-l ₂ O ₃ Content	[%]					≥ 70				
Particle Size		P 6	P 02	P 2	P 2 FR	P 30	P 2 S	P 730	P 630	P 10 feinst
≥125 µm / 120 mesh	[%]	≤ 5								
\geq 90 μm / 170 mesh	[%]		≤]	≤ 0.5	≤ 0.5	≤ 0.1				
\geq 71 μm / 200 mesh	[%]						≤ 0.1			
$\geq~63~\mu m~$ / 250 mesh	[%]	15 – 40	1.0 – 15	0.1 - 5	≤1.5	0.1 - 3	0.1 - 3			
\geq 56 μm / 270 mesh	[%]							≤ 0.1		
\geq 45 μm / 325 mesh	[%]								≤ 1.0	
$\geq~40~\mu m~$ / $400~mesh$	[%]							≤ 3		≤ 0.1
$\geq~20~\mu m~$ / $625~mesh$	[%]									≤ 3
D50 Typical	(µm)	33	16	11	24	8.3	9	3.7	3.3	3
Physical Properties										
Specific Surface Area	[m²/g]				9-	17				10-17
Loose Bulk Density	[g/l]	700 – 1000	640 — 740	500 – 800	650 — 850	500 — 800	500 — 800	400 — 600	350 — 650	350 — 550
Oil Absorption	[%]	37 - 47	36 - 46	35 - 45	40- 50	30 - 40	35 - 45	30 - 40	30- 40	30 - 40



APPLICATION: Resin-Polishing




APPLICATION: Pre-Metal-Polishing



RAPOL-Series

Aluminum oxide is the most widely used polishing medium. As a synthetic inorganic product, it has one important advantage over natural materials used for polishing: the physical properties and chemical compositions are constant regardless of the pressure or temperature experienced during use.

The RAPOL range is especially designed for one step polishing processes, which gives "rapid" cutting and shiny polishing performance. The product enables our customers to offer cost efficient solutions for their end user.



SEM of RAPOL-Series

Chemical Composition	Unit			All Sizes (Typicals		
Al ₂ O ₃ by difference	[%]			≥ 99.5		
Na ₂ O	[%]			0.1		
SiO ₂	[%]			0.02		
Calcination Degree				low		
Primary Crystal Size	(µm)			≤]		
α- A-l ₂ O ₃ Content	[%]			≥ 70		
Particle Size	Unit	RAPOL 100	RAPOL 140	RAPOL 500	RAPOL 600	RAPOL 900
\geq 125 μm / 120 mesh	[%]		≤ 0.5			
≥ 90 µm / 170 mesh	[%]		≤5	≤ 0.5		≤ 0.0
\geq 63 μm / 250 mesh	[%]	50 - 95	10 - 45	0.1 - 5.0	≤ 0.1	
\geq 45 μm / 325 mesh	[%]				≤]	≤ 0.6
D50 Typical	(µm)	70	50	11	5	0.8
Physical Properties						
Specific Surface Area	m²/g	3.5 - 4.5	3.5 - 4.5	4.0 - 8.0	4.0 - 8.0	5.0 - 9.0
Loose Bulk Density	g/l	800 - 1200	800 – 1200	500 – 900	350 - 650	300 - 650
Oil Absorption	[%]	40 - 60	35 - 50	30 - 40	25 - 35	10 - 25



ULTIMATE-Series

Automobile paints are typically two-component systems, as these protect the vehicle better against UV light and abrasion. The alumina used in the polishing emulsion should provide high cut and perfect finish to the clear coat. Almatis ULTIMATE P 815 is an economic and efficient product, giving good cut and polish. For high-end, scratch-free finishing, ULTIMATE P 2500 is the leading product in our portfolio.

In marine applications there are special requirements for the gel coat. Gel coats are very hard, modified resins that provide gloss and protect the fiberglass structure against ultraviolet degradation and hydrolysis. Polishing compounds need an aggressive cut and in parallel a good polishing performance, to achieve a smooth surface. Almatis offers specially designed aluminas for gel coat polishing, such as ULTIMATE P 1500, the best performing powder for that application.

Chemical Composition	Unit		All Sizes (Typicals)	
Al ₂ O ₃ by difference	[%]		≥ 99.7	
Na ₂ O	[%]		0.2	
SiO ₂	[%]		0.02	
Calcination Degree			low	
Primary Crystal Size	(µm)		≤ 0.5	
α- A-l ₂ O ₃ Content	[%]		99.5	
Particle Size		ULTIMATE P 815	ULTIMATE P 1500	ULTIMATE P 2500
≥ 63 µm / 250 mesh	[%]	≤ 0.1		
\geq 45 μm / 325 mesh	[%]	≤ 1.0		
\geq 20 μm / 625 mesh	[%]		≤ 3.0	≤ 0.5
D50 Typical	(µm)	9	5	2
Physical Properties				
Specific Surface Area	[m²/g]	5 - 10	4 – 8	4 - 7
Loose Bulk Density	[g/l]	300 - 600	450 - 650	
Oil Absorption	[%]	50 - 63	46 - 56	60 - 75



APPLICATION: Marine Gel Coat Polishing



APPLICATION: Clear Coat Polishing



APPLICATION: Headlight Polishing



Standard Packaging

- 10 kg / 25 kg / 50 lbs paper bags
- 900 / 1000 kg / 2500 lbs big bag, discharge sleeve and shrink wrapped (depending on bulk density)



Contacts for sales, technical information and application assistance

Almatis GmbH

Giulinistrasse 2 67065 Ludwigshafen Germany

Phone 49 621 5707 0 Fax 49 621 5707 130

Almatis B.V.

Theemsweg 30 3197KM Botlek RT The Netherlands

Phone 31 181 2701 00 Fax 31 181 2178 53

Qingdao Almatis Co. Ltd.

No.1 Song Hua Jiang Road Qingdao Economic & Technology Development Zone Qingdao, 266510 P.R. China

Phone 86 532 8572 8035 Fax 86 532 8572 8551

Almatis, Inc.

501 West Park Road Leetsdale, PA 15056, USA

Phone 1 412 630 2800 Fax 1 412 630 2900

Almatis Alumina

Private Limited

Kankaria Estate, 2nd Floor 6, Little Russell Street Calcutta 700-001, India

Phone 91 33 2242 7961 Fax 91 33 2242 1557

Almatis Limited

Morimura Bldg. Toranomon Tower Office 13 F 1-28, Toranomon 4-chrome Minato-ku, Tokyo 105-8451 Japan

Phone 81 3 5510 66 88 Fax 81 3 5510 66 80

Almatis do Brasil Ltda.

Avenida Jose de Souza Campos, 243 2° Andar – Cambuí 13025-320 – Campinas, SP – Brasil

Phone 55 19 3515-1400 Fax 55 19 3515-1410

SDS 387



Almatis GmbH

Lyoner Strasse 9 60528 Frankfurt/Germany

info@almatis.com www.almatis.com

