




Global Product Data


Super Lightweight Aggregate SLA 92

Chemical composition [wt-%]	Typical	Min.	Max.
Al ₂ O ₃	91	90	
CaO	8.5		9.2
Na ₂ O	0.40		0.5
SiO ₂	0.07		0.2
Fe ₂ O ₃	0.04		0.1
Physical properties			
Loose Bulk Density [kg/l]	0.4-0.5		
Bulk Specific Gravity [g/cm ³]	0.80		0.95
Phase Composition	CA ₆ (CaO·6 Al ₂ O ₃) CA ₂ α-Al ₂ O ₃		Major Minor Minor
Available Sizes		3 - 6 mm 1 - 3 mm 0 - 1 mm	
	Typical	Min.	Max.
	[%]	[%]	[%]
3 - 6 mm			
+ 6.30 mm	0	0	10
+ 5.00 mm	40		
+ 4.00 mm	30		
+ 3.15 mm	20		
+ 2.00 mm	10		
- 2.00 mm	0	0	10
1 - 3 mm			
+ 3.15 mm	0	0	3
+ 2.00 mm	40		
+ 1.40 mm	30		
+ 1.00 mm	20		
+ 0.71 mm	5		
- 0.71 mm	5	0	15
0 - 1 mm			
+ 1.00 mm	0	0	5
+ 0.71 mm	10		
+ 0.50 mm	15		
+ 0.25 mm	20		
+ 0.125 mm	15		
- 0.125 mm	40	10	60

All data are based upon Almatris standard test methods.



Micro Pore Size Distribution
(Hg intrusion method)



Scanning Electron Microscope Picture



Contacts for sales, technical information and application assistance

Almatris GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

☎ 49 621 5707 0
☎ 49 621 5707 130

Almatris B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

☎ 31 181 2701 00
☎ 31 181 2178 53

Almatris, Inc.

501 West Park Road
Leetsdale, PA 15056, USA

☎ 800 643 8771 General
☎ 1 412 630 2800
☎ 1 412 630 2900

Qingdao Almatris Co., Ltd.

F15, Sunshine Tower
61 Hongkong Middle Road
Qingdao, 266071
P.R. China

☎ 86 532 8572 8035
☎ 86 532 8572 8551

Qingdao Almatris Trading Co., Ltd.

Room 1807, Eton Place
69 Dong Fang Road
Shanghai, 200120
P.R. China

☎ 86 21 5879 4987
☎ 86 21 5879 6502

Almatris do Brasil Ltda.

Avenida Jose de Souza
Campos, 243
2º Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

☎ 55 19 3515-1400
☎ 55 19 3515-1410



Almatris GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatris.com
www.almatris.com

Almatris Alumina Private Limited

Kankaria Estate
2nd Floor
6, Little Russell Street
Kolkata 700-071, India

☎ 91 33 2289 4694
☎ 91 33 2289 4693

Almatris Limited

Morimura Bldg.
1-3-1 Toranomon
Minato-ku, Tokyo 105-8451
Japan

☎ 81 3 3502 2371
☎ 81 3 3502 2375

SDS 988