



Unground Calcined Aluminas

Almatis Calcined Aluminas are produced to consistently achieve the chemical purity and crystal structure necessary to meet the market needs. These products are made in rotary kilns from Bayer alumina produced in Bayer process refineries. The unground calcined aluminas may be used in some processes in their shipped form but more frequently require grinding in the customer's process.

Normal and Intermediate Soda Products

Product	A 2			A 35			CT 800			A13 LS		
	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical
Chemical Composition (%)												
Al ₂ O ₃ by difference			99.6			99.7			99.7			99.7
Na ₂ O		0.35	0.25		0.18	0.13		0.15	0.11		0.25	0.11
Fe ₂ O ₃		0.035	0.02		0.035	0.02		0.04	0.02		0.035	0.02
SiO ₂		0.03	0.02		0.03	0.01		0.03	0.01		0.03	0.02
CaO			0.03		0.06	0.03		0.06	0.03			0.03
B ₂ O ₃		0.035	0.015		0.03	0.003		0.03	0.003		0.01	0.002
Physical Properties												
Surface Area BET (m ² /g)		0.7	0.4	0.35	0.7	0.5	0.65	0.85	0.7	6.5	15.0	9
LOI 300 to 1100°C (%)			0.2									
Green Density ⁽¹⁾ (g/cc)						2.27	2.22	2.34	2.28			
Particle Size												
+100M ⁽²⁾ /0.150mm (%)			0-8			0-8			0-8			0-8
+200M ⁽²⁾ /0.075mm (%)			40-80			40-80			40-80			40-80
+325M ⁽²⁾ /0.045mm (%)			70-95			70-95			70-95			70-95
Packaging												
See Std. Packaging (p2)		1, 2, 3, 4, 6			1, 2, 3, 4, 6			1, 3, 4, 6			1, 3, 4, 6	

(1) By Lab Grind

(2) Tyler Mesh



Unground Calcined Aluminas

Low Soda Products

Product	A 3500			A 10			CL 3000			A 14		
	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical	Min	Max	Typical
Chemical Composition (%)												
Al ₂ O ₃ by difference			99.8			99.7			99.8			99.8
Na ₂ O		0.10	0.08		0.13	0.08		0.08	0.04		0.05	0.03
Fe ₂ O ₃		0.035	0.02		0.05	0.02		0.04	0.02		0.05	0.01
SiO ₂		0.03	0.01		0.12	0.04		0.04	0.02		0.05	0.02
CaO		0.06	0.02			0.03		0.06	0.03		0.06	0.03
B ₂ O ₃		0.03	0.002		0.22	0.10		0.05	0.02		0.06	0.03
Physical Properties												
Surface Area BET (m ² /g)	0.35	0.60	0.5			0.2	0.60	0.75	0.7	0.45	0.70	0.55
Green Density ⁽¹⁾ (g/cc)			2.27				2.24	2.32	2.27			2.31
Particle Size												
Cilas d50 ⁽¹⁾ (µm)	2.1	3.0	2.3	4.2	5.2	4.8	1.4	2.2	1.7	1.6	2.4	1.9
Packaging												
See Std. Packaging (below)	1, 2, 3, 4, 6			1, 4, 5, 6			4, 5, 6			1, 2, 3, 4, 6		

(1) By Lab grind

Standard Packaging

- 50 lb paper bags - 70 per pallet
- 25 kg paper bags - 40 per pallet
- 2500 lb super sacks - 1 per pallet
- 1 mt super sacks - 1 per pallet
- 2755 lb super sacks - 1 per pallet
- Bulk rail car
- Other options available with upcharge

All data is based upon Almatis standard test methods. All test methods are available upon request. The typical properties are based upon the actual averages from production data. The Min/Max data represents Almatis standard product specification data for these products.



Contacts for sales, technical information and application assistance

Almatis GmbH
Lyoner Straße 9
60528 Frankfurt/Germany
Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatis.com
www.almatis.com

Almatis, Inc.
501 West Park Road
Leetsdale, PA 15056, USA
Phone
800 643 8771 General
1 412 630 2800
Fax
1 412 630 2900

Almatis do Brasil Ltda.
Avenida Jose de Souza
Campos, 243
2º Andar – Cambuí
13025-320 – Campinas,
SP – Brasil
Phone
55 19 3515-1400
Fax
55 19 3515-1410

SDS 387