



## Global Product Data

# CT 3000 LS SG

### Product Description

Almatis Alumina CT3000 LS SG is a special purpose low soda high reactive alumina. It combines high fired density with very low impurities.

### Product Features

High fired density > 3,90 g/cm<sup>3</sup> at 1540 °C 1 hour soak time and > 3,94 g/cm<sup>3</sup> at 1600 °C 1 hour soak time. Very low impurities.

### Applications

High end ceramic pieces where high sintered density and low impurities are required.

| Chemical Analysis              |     | typical |
|--------------------------------|-----|---------|
| Al <sub>2</sub> O <sub>3</sub> | [%] | 99.8    |
| Na <sub>2</sub> O              | [%] | 0.03    |
| Fe <sub>2</sub> O <sub>3</sub> | [%] | 0.015   |
| SiO <sub>2</sub>               | [%] | 0.015   |
| MgO                            | [%] | 0.040   |
| CaO                            | [%] | 0.015   |

| Properties                        | typical   |
|-----------------------------------|---|
| Specific Surface area / BET       | 7.80 m <sup>2</sup> /g                          |
| Particle Size / D50 Cilas         | 0.5 µm  |
| Particle Size / D90 Cilas         | 2.0 µm  |
| Green density (90 MPa)            | 2.24 g/cm <sup>3</sup>                          |
| Fired density (1540 °C / 1600 °C) | 3.91 g/cm <sup>3</sup> / 3.95 g/cm <sup>3</sup> |
| Shrinkage (1540 °C / 1600 °C)     | 16.8% / 17.3%                                   |

All data are based upon Almatis standard test methods.

The typical properties are based upon the actual averages from production data.



# CT 3000 LS SG

## Standard Packaging

- 25 kg paper bags on 1 mt pallet
- 1000 kg big bag, discharge sleeve and shrink wrapped



## Contacts for sales, technical information and application assistance

**Almatis GmbH**  
Giuliniestr. 2  
67065 Ludwigshafen  
Germany

☎ 49 621 5707 0  
☎ 49 621 5707 130

**Almatis B.V.**  
Theemsweg 30  
3197KM Botlek RT  
The Netherlands

☎ 31 181 2701 0  
☎ 31 181 2178 53

**Almatis, Inc.**  
501 West Park Road  
Leetsdale, PA 15056, USA

☎ 800 643 8771 General  
☎ 1 412 630 2800  
☎ 1 412 630 2900

**Qingdao Almatis Co., Ltd.**  
F15, Sunshine Tower  
61 Hongkong Middle Road  
Qingdao, 266071  
P.R. China

☎ 86 532 8572 8085  
☎ 86 532 8572 8551

**Qingdao Almatis Trading Co., Ltd.**  
Room 1807, Eton Place  
69 Dong Fang Road  
Shanghai, 200120  
P.R. China

☎ 86 21 5879 4887  
☎ 86 21 5879 6502

**Almatis do Brasil Ltda.**  
Avenida Jose de Souza  
Campos, 243  
2° Andar – Cambuí  
13025-320 – Campinas,  
SP – Brasil

☎ 55 19 3515-1400  
☎ 55 19 3515-1410



Almatis GmbH  
Lyoner Straße 9  
60528 Frankfurt/Germany  
Phone 49 69 957 341 0  
Fax 49 69 957 341 13

[info@almatis.com](mailto:info@almatis.com)  
[www.almatis.com](http://www.almatis.com)

**Almatis Alumina Private Limited**  
Kankaria Estate  
2nd Floor  
6, Little Russell Street  
Kolkata 700-071, India  
☎ 91 33 2289 4694  
☎ 91 33 2289 4693

**Almatis Limited**  
Morimura Bldg.  
1-3-1 Toranomon  
Minato-ku, Tokyo 105-8451  
Japan  
☎ 81 3 3502 2371  
☎ 81 3 3502 2375

## MSDS 387