



ALMATIS
PREMIUM ALUMINA



Global Product Data

Calcined Aluminas for Polishing



Think alumina, think Almatris.

GP-RCP/007/R14/0319/SDS 387



Calcined Aluminas for Polishing

Product / Properties		PG feinst	P 815/P 816	A 13 LS	A 13 – 325
Unground	Unit	typ.	typ.	typ.	typ.
Calcination degree		very low	very low	low	low
Primary crystal size	µm	< 0.1	< 1	< 1	< 1
α - Al ₂ O ₃ content	%	0	> 70	> 70	> 70
Chemical Analysis					
Na ₂ O	%	0.5	0.3	0.1	0.1
Fe ₂ O ₃	%	0.03	0.02	0.02	0.02
SiO ₂	%	0.03	0.02	0.02	0.02
Particle Size					
> 150 µm / 100 mesh	%			4	
> 71 µm / 200 mesh	%			60	
> 45 µm / 325 mesh	%		0.8	85	6
> 20 µm / 635 mesh	%	< 3			
d10 Cilas / Compacite	µm	0.7	1.2		0.6
d50 Cilas / Compacite	µm	3.4	6	80	4.5
d90 Cilas / Compacite	µm	14	20		28
Specific surface area / BETm ² /g		45 – 80	5 – 12	6.5 – 15	8 – 17
Loose bulk density	g/l	450 – 600			650
Oil absorption	%	35 – 50	53	52	30
Cutting effect		1	1	2	2
Polishing effect		10	10	7	9

All data are based on Almatix test methods, measured with Cilas 1064 and published as typical or rang limits.

produced in North America

produced in Europe

General information:

- Al₂O₃: min. 99%
- specific gravity: 3.98 g/cm³

Calcined Aluminas for Polishing

Product / Properties Unground	Unit	P 10 typ.	P 6 typ.	P 02 typ.	P 2 typ.	P 2 FR typ.	P 30 typ.	P 2 S typ.	P 730 typ.	P 10 feinst typ.
Calcination degree		low	low	low	low	low	low	low	low	low
Primary crystal size	µm	< 1	< 1	< 1	< 1	< 1	< 1	< 1	< 1	< 1
α - Al ₂ O ₃ content	%	> 70	> 70	> 70	> 70	> 70	> 70	> 70	> 70	> 70
Chemical Analysis										
Na ₂ O	%	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4	0.4
Fe ₂ O ₃	%	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
SiO ₂	%									
Particle Size										
> 200 µm / 65 mesh	%	< 0.1								
> 125 µm / 115 mesh	%		< 5							
> 90 µm / 170 mesh	%			< 1	< 0.5	< 0.5	< 0.1			
> 71 µm / 200 mesh	%							< 0.1		
> 63 µm / 250 mesh	%	25 – 50	15 – 40	1.0 – 15	0.1 – 5	< 1.5	0.1 – 3	0.1 – 3		
> 56 µm / 270 mesh	%								< 0.1	
> 40 µm / 400 mesh	%								< 3	< 0.1
> 20 µm / 635 mesh	%									< 3
d10 Cilas	µm	1.6	1.5	1	0.8	1.2	0.7	0.7	0.6	0.5
d50 Cilas	µm	38	33	16	11	24	8,3	9	3,7	3
d90 Cilas	µm	100	90	48	40	45	36	34	19	14
Specific surface area / BETm ² /g		9 – 17	9 – 17	9 – 17	9 – 17	9 – 17	9 – 17	9 – 17	9 – 17	10 – 17
Loose bulk density	g/l	700 – 1000	700 – 1000	640 – 740	500 – 800	650 – 850	500 – 800	500 – 800	400 – 600	350 – 550
Oil absorption	%	38 – 50	37 – 47	36 – 46	35 – 45	40 – 50	30 – 40	35 – 45	30 – 40	30 – 40
Cutting effect		2	3	2	2	2	2	2	2	2
Polishing effect		7	8	8	9	9	9	9	9	10

All data are based on Almatix test methods, measured with Cilas 1064 and published as typical or rang limits.

produced in North America

produced in Europe

General information:

- Al₂O₃: min. 99%
- specific gravity: 3.98 g/cm³



Calcined Aluminas for Polishing

Product / Properties	Unit	WRA	P 66 M	WRA FG	PSG 100	PSG 110	PSG 125	PSG 140	PSG 150	PSG 300
Unground		typ.	typ.	typ.	typ.	typ.	typ.	typ.	typ.	typ.
Calcination degree		medium high	medium high	medium high	high	high	high	high	high	high
Primary crystal size	µm	2.5	2.5	2.5	3	3	3	3	3	3
α - Al ₂ O ₃ content	%	99	99	99	99	99	99	99	99	99
Chemical Analysis										
Na ₂ O	%	0.12	0.2	0.12	0.15	0.25	0.15	0.15	0.15	0.15
Fe ₂ O ₃	%	0.02	0.02	0.02	0.03	0.02	0.03	0.03	0.03	0.03
SiO ₂	%	0.01	0.02	0.02		0.02		0.02		
Particle Size										
> 200 µm / 65 mesh	%	< 5			< 1					
> 150 µm / 100 mesh						< 2.0				
> 125 µm / 115 mesh	%		< 5				< 4	< 0.5	< 0.1	
> 90 µm								< 5		
> 63 µm / 250 mesh	%	50 – 95	< 15		50 – 95		30 – 60	10 – 35	< 3	
> 45 µm / 325 mesh	%			< 3		84 – 96				
> 40 µm / 325 mesh	%									< 3
d10 Cilas / Compacite	µm		0.3	0.4		14	17		0.2	0.6
d50 Cilas / Compacite	µm	70	5	4	86	80	65	50	5	4.9
d90 Cilas / Compacite	µm		40	14		130	100		26	17
Specific surface area / BET m ² /g		0.5 – 0.7	0.6 – 1.5	0.6 – 1.1	0.4 – 0.55	0.4 – 0.7	0.4 – 0.55	0.4 – 0.6	0.4 – 0.6	0.55 – 0.75
Loose bulk density	g/l	700 – 1100	760 – 950	600 – 900	800 – 1050	750 – 950	800 – 1050	700 – 1000	700 – 950	550 – 900
Oil absorption	%	40 – 60	14 – 25	12 – 25	41 – 54	40 – 55	35 – 50	35 – 50	12 – 25	12 – 22
Cutting effect		6	4	4	9	9	8	8	7	6
Polishing effect		3	4	5	3	3	3	3	3	4

All data are based on Almatix test methods, measured with Cilas 1064 and published as typical or rang limits.

produced in North America

produced in Europe

General information:

- Al₂O₃: min. 99%
- specific gravity: 3.98 g/cm³

Calcined Aluminas for Polishing

Product / Properties	Unit	A 2 typ.	A 267 typ.	A 2 – 325 typ.	A 2–325 CR typ.	A 35 – 325 typ.
Calcination degree		high	high	high	high	very high
Primary crystal size	µm	3	3	2.5	2.5	2.5
α - Al ₂ O ₃ content	%	99	99	99	99	99
Chemical Analysis						
Na ₂ O	%	0.25	0.25	0.25	0.25	0.11
Fe ₂ O ₃	%	0.02	0.02	0.02	0.02	0.02
SiO ₂	%	0.02	0.02	0.021	0.03	0.02
Particle Size						
> 150 µm / 100 mesh	%	3				
> 71 µm / 200 mesh	%	58				
> 45 µm / 325 mesh	%	83	20 – 40	< 5	< 1	< 5
d10 Cilas	µm	40	4	0.6	0.4	0.9
d50 Cilas	µm	73	20	6	5	5.6
d90 Cilas	µm	90	42	14	12	17
Specific surface area / BET m ² /g		< 0.8	0.5 – 1.5	< 1.1	< 1.1	< 1.1
Loose bulk density	g/l	825	875	925	950	925
Oil absorption	%	50	50	20	15	20
Cutting effect		9	8	7	6	7
Polishing effect		3	3	3	4	3

All data are based on Almatis test methods, measured with Cilas 1064 and published as typical or rang limits.

produced in North America

produced in Europe

General information:

- Al₂O₃: min. 99%
- specific gravity: 3.98 g/cm³



Calcined Aluminas for Polishing

Product / Properties	Unit	CT 19 typ.	PBC typ.	PB typ.	P 20 typ.	P 25 typ.	Gilox 63 typ.	Gilox 125 typ.	A 10 5 µm typ.	A 10 – 325 typ.
Calcination degree		very high	very high	very high	very high	very high	very high	very high	very high	very high
Primary crystal size	µm	4.5	4.5	4.5		22	15	12	5	5
α - Al ₂ O ₃ content	%	99	99	99	99	99	99	99	99	99
Chemical Analysis										
Na ₂ O	%	0.06	0.1	0.1	0.35	0.35	0.35	0.35	0.08	0.08
Fe ₂ O ₃	%	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.02	0.02
SiO ₂	%	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.03	0.04
Particle Size										
> 150 µm / 100 mesh	%	<10	< 5	< 3					1	
> 125 µm / 115 mesh	%							< 1		
> 71 µm / 200 mesh	%								57	
> 63 µm / 250 mesh	%	50 – 95	40 – 90	40 – 90	50 – 80	55 – 90	0.1 – 3	5 – 12		
> 45 µm / 325 mesh	%								87	< 5
d10 Cilas	µm				4*	5*	2.5		50	1.2
d50 Cilas	µm	65	68	65	18*	25*	17	21.5	82	8.3
d90 Cilas	µm				55*	70*	45		130	20
Specific surface area / BET m ² /g		0.2 – 0.45	0.3 – 0.45	0.3 – 0.45	0.15	0.15	0.2		0.2 – 0.6	0.4 – 0.9
Loose bulk density	g/l	750 – 1050	800 – 1100	750 – 1050	600 – 1100	600 – 1100			950	800
Oil absorption	%	40 – 50	40 – 46	37 – 44	20 – 60	25 – 65	10 – 25	15 – 30	35	15
Cutting effect		8	8	8	9	9	8	8	8	7
Polishing effect		2	3	3	1	1	1	1	2	3

All data are based on Almatix test methods, measured with Cilas 1064 and published as typical or rang limits.

produced in North America

produced in Europe

General information:

- Al₂O₃: min. 99%
- specific gravity: 3.98 g/cm³
- * desagglomerated

Calcined Aluminas for Polishing

What are polishing aluminas?

Our polishing aluminas are grades of a specially produced oxide. As inorganic products, they have one important advantage over natural materials used for polishing: their physical properties and chemical compositions are constant regardless of the pressure or temperature experienced during use. Aluminum oxide is the most widely used polishing medium. In general, polishing compounds contain approximately 50% alumina. The aluminum oxide is in the form of an agglomerate that consists of numerous primary crystals. The size of these crystals depends on the degree of calcination: as a general rule, the higher the calcination temperature, the larger the primary crystals. Certain grades with larger crystals can be used for grinding and lapping while some with small primary crystals simply equalize and smooth the surface being treated, without removing significant amounts of material. The primary crystals of Almatis polishing aluminas are extremely hard. On the Mohs scale the aluminas rate one degree below diamond.

What are the properties of Almatis polishing aluminas?

Almatis polishing aluminas are used in many different applications and industrial processes. They give excellent results in lapping and grinding situations. They are successfully used in various lapping processes as precision lapping, final lapping, surface abrasion (hydro abrasion) and polishing (buffing, hydro lapping, barrel polishing resp. tumbling). They can also be used successfully in grinding processes where a certain amount of cutting always takes place leaving a rough surface. Typical applications are in honing, super finishing, fettling and polishing (using polishing wheels). The main benefits of Almatis polishing aluminas are:

- Crushing properties of the agglomerates and primary crystals
- Hardness of the primary crystals
- Shape of the grains in the damaged and the undamaged crystals
- Wide range of working temperature, high melting point and excellent resistance to thermal shock
- Workability and oil absorption
- Homogeneity of the powder low in impurities, hard particles

The balance of cutting and polishing effects, together with the oil absorption rate, indicates where each grade of polishing alumina can be used most effectively. The cutting effect is indicated on a scale of 1 to 10, where 1 represents a low cut and 10 represents a very high degree of abrasion. The polishing effect is classified in the same way, with the scale number 1 indicating a highly reflective surface finish and scale number 10 indicating a lustrous finish achieved by fine, soft aluminas.

How are they applied?

Almatis polishing aluminas are used alone or as an ingredient of a polishing compound. These compounds are effectively a mixture of a polishing medium with a binder, usually oil or wax. The ratio of binder to a polishing medium varies according to the intended application but is usually in the region of 50% polishing medium, 50% binder. The most common forms in which Almatis polishing aluminas are applied are:

- As is, without any additives
- As a suspension in water or oil
- Mixed with water or oil emulsions
- Mixed with a creamy paste
- Mixed with a solid paste to form a polishing bar

They can be applied manually or in automatic polishing processes, such as airless processes or barrel finishing. Other applications are household cleaners, car cleaners, stone polishes, brake linings and vibro-finishing.



Calcined Aluminas for Polishing



Contacts for sales, technical information and application assistance

Almatis GmbH

Giulinistrasse 2
67065 Ludwigshafen
Germany

☎ 49 621 5707 0

☎ 49 621 5707 130

Almatis B.V.

Theemsweg 30
3197KM Botlek RT
The Netherlands

☎ 31 181 2701 00

☎ 31 181 2178 53

Almatis, Inc.

501 West Park Road
Leetsdale, PA 15056, USA

☎ 800 643 8771 General

☎ 1 412 630 2800

☎ 1 412 630 2900

Almatis do Brasil Ltda.

Avenida Jose de Souza
Campos, 243
2º Andar – Cambuí
13025-320 – Campinas,
SP – Brasil

☎ 55 19 3515-1400

☎ 55 19 3515-1410

Qingdao Almatis Co., Ltd.

No.1, Songhuanjiang Road
Huangdao District
Qingdao, 266555
P.R. China

☎ 86 21 5879 4987

☎ 86 21 5879 6502

**Almatis Alumina
Private Limited**

Kankaria Estate
2nd Floor
6, Little Russell Street
Kolkata 700-071, India

☎ 91 33 2289 4694

☎ 91 33 2289 4693



Almatis GmbH
Lyoner Straße 9
60528 Frankfurt/Germany

Phone 49 69 957 341 0
Fax 49 69 957 341 13

info@almatis.com
www.almatis.com

Almatis Limited

Toranomon Towers Office 13F
1-28, Toranomon 4-chrome,
Minato-ku, Tokyo, 105-8451
Japan

☎ 81 3 3432 6121

☎ 81 3 3432 6125

SDS 387